

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 0 922 082 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention
of the grant of the patent:
14.05.2003 Bulletin 2003/20

(51) Int Cl.7: **C11D 3/00, C11D 1/00,
C11D 1/14, C11D 3/37,
C11D 3/12**

(21) Application number: **97937221.6**

(86) International application number:
PCT/US97/14224

(22) Date of filing: **13.08.1997**

(87) International publication number:
WO 98/006801 (19.02.1998 Gazette 1998/07)

(54) FABRIC CLEANING FORMULATIONS

REINIGUNGSMITTEL FÜR GEWEBE

PREPARATIONS NETTOYANTES POUR TISSU

(84) Designated Contracting States:
BE DE FR GB IT NL

• **STRICKLER, Charles, Leonard**
Elkton, MD 21921 (US)

(30) Priority: **16.08.1996 US 699085**

(74) Representative: **Carpmaels & Ransford**
43 Bloomsbury Square
London WC1A 2RA (GB)

(43) Date of publication of application:
16.06.1999 Bulletin 1999/24

(73) Proprietor: **E.I. DU PONT DE NEMOURS AND
COMPANY**
Wilmington Delaware 19898 (US)

(56) References cited:
WO-A-95/34631 US-A- 3 716 488
US-A- 3 901 727 US-A- 4 035 148
US-A- 4 925 707 US-A- 5 439 610

(72) Inventors:
• **MATERNIAK, Joyce, Monson**
Hockessin, DE 19707 (US)

Remarks:

The file contains technical information submitted
after the application was filed and not included in this
specification

EP 0 922 082 B1

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

Description

Field of the Invention

- 5 [0001] This invention relates to fabric cleaning compositions of the type adaptable for use in the shampooing and cleaning of textile fabrics such as carpets, and more particularly to fabric cleaning compositions that inhibit resoiling and restaining after cleaning.

Background of the Invention

- 10 [0002] Fabric cleaning formulations have been previously developed and employed in the cleaning of textile fabrics, including upholstery, leather and pile fabrics of the type normally found in carpets and rugs. Many of the prior fabric cleaning formulations involve the use of detergent materials in aqueous or solvent mediums, in which dirt and soil are removed by normal detergent action. Others involve formulations which are applied dry or damp to the fabric surface.
- 15 [0003] A disadvantage to many of the previous cleaning formulations is the tendency of the shampooed area to resoil or restain soon after cleaning. In many instances, residue from fabric cleaning formulations of the prior art seem to attract soil and stains to the cleaned textile fabric.
- 20 [0004] Others have tried to solve this resoiling problem by modifying fabric cleaning compositions with additives to prevent resoiling such as various types of fluorochemicals. See, for example, U.S. Patent Nos. 4,043,964; 4,279,796; 5,338,475; 5,395,555. Still others have modified fabric cleaning compositions with stain resist agents, such as styrene maleic anhydride, methylmethacrylate, methacrylic acid and the like. See, for example, U.S. Patent Nos. 3,716,488; 3,723,323; 3,779,929; 3,835,071; 4,203,859; 4,566,980; 4,678,595; 4,908,149. Still others have modified fabric cleaning compositions with inorganic particles such as clays, silicas and alumina to improve resoiling. See, for example, U.S. Patent Nos. 3,716,488; 3,736,259; 4,035,148; 4,090,974; 4,566,980; 4,581,385; 4,873,000. While all of these modifications improve resoiling or restaining vs. the unmodified fabric cleaning formulation, there is still some degree of resoiling or restaining.
- 25 [0005] Others have tried to solve this problem by combining soil resist agents and stain resist agents in a single fabric cleaning formulation. See, for example, U.S. Patent Nos. 3,901,727; 4,043,923; 5,073,442; 5,212,272; 5,439,610 and Japanese Kokai 56-129281. Resoiling and restaining are further improved, but there is still room for improvement. Furthermore, it would be advantageous if once textile fabrics were cleaned that they resisted resoiling and restaining better than they had resisted soiling or staining prior to cleaning.
- 30 [0006] Accordingly, it is an object of this invention to provide an improved textile fabric cleaning composition which imparts to the fabric improved soil and stain-resistance after cleaning.
- 35

Summary of the Invention

- 40 [0007] This invention provides aqueous cleaning formulations comprising 4 to 270 grams (or 1.3 to 270 grams on a 100% active ingredient basis) of detergent per 3.79 l (gallon) of cleaning formulation, 0.04 to 133 grams (or 0.009 to 60 grams on a 100% active ingredient basis) of a fluorochemical soil-resist agent per 3.79 l (gallon) of cleaning formulation, 0.7 to 536 grams (or 0.2 to 134 grams on a 100% active ingredient basis) of a stain-resist agent per 3.79 l (gallon) of cleaning formulation, and 0.04 to 133 grams (or 0.01 to 53 grams on a 100% active ingredient basis) of inorganic particulate matter selected from the group consisting of clays, colloidal silica, colloidal alumina, titanium dioxide, and mixtures thereof. The detergent may contain an anionic, cationic, amphoteric, or nonionic surfactant.
- 45 Preferred detergents include a mixture of sodium tripolyphosphate and sodium sesquicarbonate; or a mixture of sodium lauryl sulfate, sodium hexadecyl sulfate and sodium tetradecyl sulfate. The stain-resist agent may be selected from the group consisting of copolymers of hydrolyzed maleic anhydride with aliphatic alpha olefins, aromatic olefins, or vinyl ethers, homopolymers of methacrylic acid, and copolymers of methacrylic acid. In one preferred formulation, the detergent is a mixture of sodium tripolyphosphate and sodium sesquicarbonate, and the inorganic particulate matter is colloidal silica. In another preferred formulation, the detergent is a mixture of sodium lauryl sulfate, sodium hexadecyl sulfate and sodium tetradecyl sulfate, and the inorganic particulate matter is colloidal silica.
- 50 [0008] This invention also includes cleaning concentrates suitable for making an aqueous cleaning formulation comprising (a) a surfactant, (b) a fluorochemical soil-resist agent, (c) a stain-resist agent, and (d) inorganic particulate matter selected from the group consisting of clays, colloidal silica, colloidal alumina, titanium dioxide, and mixtures thereof, whereby the concentrate is capable of being diluted with an appropriate amount of water to produce an aqueous cleaning formulation having a concentration of 4 to 270 grams (or 1.3 to 270 grams on a 100% active ingredient basis) of detergent per 3.79 l (gallon) of cleaning formulation, 0.04 to 133 grams (or 0.009 to 60 grams on a 100% active
- 55

ingredient basis) of a fluorochemical soil-resist agent per 3.79l (gallon) of cleaning formulation, 0.7 to 536 grams (or 0.2 to 134 grams on a 100% active ingredient basis) of a stain-resist agent per 3.79l (gallon) of cleaning formulation, and 0.04 to 133 grams (or 0.01 to 53 grams on a 100% active ingredient basis) of inorganic particulate matter selected from the group consisting of clays, colloidal silica, colloidal alumina, titanium dioxide, and mixtures thereof per 3.79l (gallon) of cleaning formulation. The detergent may contain an anionic, cationic, amphoteric, or nonionic surfactant. Preferred detergents include a mixture of sodium tripolyphosphate and sodium sesquicarbonate; or a mixture of sodium lauryl sulfate, sodium hexadecyl sulfate and sodium tetradecyl sulfate. The stain-resist agent in the concentrate may be a compound selected from the group consisting of copolymers of hydrolyzed maleic anhydride with aliphatic alpha olefins, aromatic olefins, or vinyl ethers, homopolymers of methacrylic acid, and copolymers of methacrylic acid. In one preferred cleaning concentrate, the detergent is a mixture of sodium tripolyphosphate and sodium sesquicarbonate, and the inorganic particulate matter is colloidal silica. In another preferred concentrate, the detergent is a mixture of sodium lauryl sulfate, sodium hexadecyl sulfate and sodium tetradecyl sulfate, and the inorganic particulate matter is colloidal silica.

[0009] This invention also includes methods for cleaning textile fabrics comprising fibers having soil on the fiber surfaces. The steps involved in such methods comprise contacting the fibers with an aqueous cleaning formulation comprising a detergent, a fluorochemical soil-resist agent, a stain-resist agent, and inorganic particulate matter selected from the group consisting of clays, colloidal silica, colloidal alumina, titanium dioxide, and mixtures thereof in a concentration of: (a) 0.07 to 5% (or 0.02 to 5% on a 100% active ingredient basis) of detergent based on weight of fiber, (b) 0.0008 to 10% (or 0.0002 to 4.5% on a 100% active ingredient basis) of fluorochemical soil-resist agent based on weight of fiber, (c) 0.01 to 15% (or 0.0025 to 3.75% on a 100% active ingredient basis) of stain-resist agent based on weight of fiber, and (d) 0.0008 to 10% (or 0.0003 to 4.0% on a 100% active ingredient basis) of inorganic particulate matter based on weight of fiber in such a manner that at least some of the soil on the fiber surfaces is loosened, followed by removing at least some of the loosened soil. The above-described aqueous cleaning formulations with the specified detergents, fluorochemical soil-resist agents, stain-resist agents, and inorganic particulate matter may be used in such cleaning methods.

[0010] In a preferred hot water extraction method, the fibers of the fabric are contacted with the aqueous cleaning formulation by spraying the formulation having a temperature in the range of room temperature to 71°C (160°F) onto the fibers. In other methods, the cleaning formulation may be foam applied or applied with a device such as a wetted pad or brush. The textile fabric to be cleaned may be selected from a variety of fabric materials such as upholstery or carpets, particularly nylon carpets.

Detailed Description of the Invention

[0011] The textile fabric cleaning compositions of this invention contain a) detergent, b) fluorochemical soil-resist agent, c) stain-resist agent, and d) a stable aqueous dispersion of inorganic particulate matter selected from the group consisting of clay, colloidal silica, colloidal alumina, titanium dioxide, and mixtures thereof.

[0012] By "detergent", it is meant compositions which reduce the surface tension of water; specifically, a surface-active agent which concentrates at oil-water interfaces, exerts emulsifying action, and thus aids in removing soils. Preferably, the detergent contains one or more surfactants (which may be hydrocarbon or fluorocarbon) to provide greater cleaning strength. These surfactants include anionic, cationic, amphoteric or nonionic surfactants or a mixture thereof. Such compounds as alkyl sulfonates, phosphates, glycols, and the like are typically used. Sodium lauryl sulfate, and sodium tripolyphosphate/sodium sesquicarbonate aqueous solutions are preferred detergents. A particularly preferred detergent is a mixture of about 90-95% by weight sodium tripolyphosphate and about 5-10% by weight sodium sesquicarbonate. Such a mixture is available from Stanley Steemer as Stanley Steemer Carpet Cleaner SS-76®, hereinafter referred to as "SS-76®". An aqueous solution comprising a mixture of sodium lauryl sulfate, sodium hexadecyl and sodium tetradecyl sulfate (available from Witco as DuPanol® WAQE) is also an effective detergent. The detergents may also contain detergent builders such as ethylenediaminetetraacetic acid (EDTA).

[0013] By "fluorochemical soil-resist agent" it is meant compositions which resist or repel dirt, oil, or other substances not normally intended to be present on a substrate such as a textile material. Fluorochemical soil-resist agents may include polymers or compounds having pendent or end groups of perfluoroalkyl moieties, fluorosurfactants, or fluoro-intermediates. Examples of some suitable fluorochemical soil-resist agents include Zonyl® 7950 and Zonyl® 5180 (available from DuPont).

[0014] By "stain-resist agent" it is meant chemicals which impart partial or total resistance to staining. Staining is defined as discoloration due to a material adding color (such as food or liquid) that exhibits resistance to removal by standard cleaning methods. Stain-resist agents may include compounds such as hydrolyzed maleic anhydride co- or terpolymers with aliphatic alpha olefins, aromatic olefins or vinyl ethers, and homo- or copolymers of methacrylic acid. Preferably, the stain-resist agent is Zelan® 338 which is available from DuPont.

[0015] By "inorganic particulate matter" it is meant compounds selected from the group consisting of clays, colloidal

silica, colloidal alumina, titanium dioxide and combinations thereof. Colloidal silica such as Ludox® HS-40 (available from DuPont) is especially preferred.

[0016] The relative amounts of detergent, fluorochemical soil-resist agent, stain-resist agent, and stable aqueous dispersion of inorganic particulate matter in the cleaning formulations of this invention vary depending on the chemicals used. Generally, the formulation comprises:

- a) 0.07 to 5% based on weight of fiber (% owf) of detergent,
- b) 0.0008 to 10% owf of fluorochemical soil-resist agent,
- c) 0.01 to 15% owf of stain-resist agent; and
- d) 0.0008 to 10% owf of inorganic particulate matter.

[0017] The above ranges for the chemical components of the formulation are based on the components as-delivered. With as-delivered components, the active ingredient in the components may be less than 100%. On a 100% active ingredient basis, the cleaning formulation comprises 0.02 to 5.0% on weight of fiber (% owf) of detergent, 0.0002 to 4.5% owf of fluorochemical soil-resist agent, 0.0025 to 3.75% owf stain-resist agent, and 0.0003 to 4.0% owf inorganic particulate matter.

[0018] Alternatively, the concentration of the components in the aqueous cleaning formulations of this invention may be expressed in terms of grams per 3.79 l (gallon) of cleaning formulation. Particularly, the formulation comprises 4 to 270 grams (or 1.3 to 270 grams on a 100% active ingredient basis) of detergent per 3.79 l (gallon) of cleaning formulation, 0.04 to 133 grams (or 0.009 to 60 grams on a 100% active ingredient basis) of fluorochemical soil-resist agent per 3.79 l (gallon) of cleaning formulation, 0.7 to 536 grams (or 0.2 to 134 grams on a 100% active ingredient basis) of stain-resist agent per 3.79 l (gallon) of cleaning formulation, and 0.04 to 133 grams (or 0.01 to 53 grams on a 100% active ingredient basis) of inorganic particulate matter selected from the group consisting of clays, colloidal silica, colloidal alumina, titanium dioxide, and mixtures thereof.

[0019] The aqueous cleaning formulations of this invention may also contain other chemical agents known in the art such as fragrances, water softeners, pH buffers, and brighteners.

[0020] As described above, the aqueous cleaning formulations of this invention refer to the formulations as they are applied to textile fabrics such as carpets. It is recognized that cleaning concentrates suitable for making the aqueous cleaning formulations of this invention by dilution with water can also be made. These cleaning concentrates would then be provided to the carpet cleaner or other end-user. This invention also encompasses such cleaning concentrates. The cleaning concentrate comprises: (a) a detergent, (b) a fluorochemical soil-resist agent, (c) a stain-resist agent, and (d) inorganic particulate matter selected from the group consisting of clays, colloidal silica, colloidal alumina, titanium dioxide, and mixtures thereof, whereby the concentrate is capable of being diluted with an appropriate amount of water to produce an aqueous cleaning formulation having a concentration of 4 to 270 grams (or 1.3 to 270 grams on a 100% active ingredient basis) of detergent per 3.79 l (gallon) of cleaning formulation, 0.04 to 133 grams (or 0.009 to 60 grams on a 100% active ingredient basis) of a fluorochemical soil-resist agent per 3.79 l (gallon) of cleaning formulation, 0.7 to 536 grams (or 0.2 to 134 grams on a 100% active ingredient basis) of a stain-resist agent per 3.79 l (gallon) of cleaning formulation, and 0.04 to 133 grams (or 0.01 to 53 grams on a 100% active ingredient basis) of inorganic particulate matter.

[0021] The cleaning formulations of this invention effectively remove soil and many stains from textile fabrics and leave the fabric with an enhanced resistance to resoiling and restaining. Generally, the cleaning method involves contacting a textile fabric made of fibers with soil on the fiber surfaces, such as soiled upholstery or carpet, with the aqueous cleaning formulation in such a manner that at least some of the soil on the fiber surfaces is removed. A dispersion containing some of the loosened soil in the formulation may be formed. The loosened soil is removed by a suitable means such as vacuuming or padding. The preferred method for cleaning textile fabrics with the cleaning formulations of this invention is by hot water extraction. This method involves spraying the selected cleaning formulation having a temperature in the range of room temperature to 71°C (160°F) onto the fibers of the textile fabric. Alternatively, other cleaning methods may be used which include, but are not limited to, water extraction, foam cleaning, spin bonnet, and spot cleaning. In some methods, the cleaning formulation is applied by a wetted device such as a pad or brush. The best results occur when all loose soil and stain is removed by vacuuming or other means prior to application of the cleaning formulations.

[0022] The following examples further illustrate the invention but should not be construed as limiting the scope of the invention.

Test Methods**Stain Performance After Carpet Cleaning**

- 5 [0023] Carpets were cleaned with the cleaning formulations described in the following examples and allowed to completely dry. Each carpet was then stained with cherry flavored Kool-Aid® for one hour, rinsed with tap water and dried. The carpets were then rated for stain-resistance using the AATCC test method 175 stain scale, where 1=severely stained and 10=no staining.

Soil Performance After Carpet Cleaning

- 10 [0024] The carpet samples were cleaned with the cleaning formulations as described in the following examples and allowed to completely dry. Unless otherwise indicated in the examples, each carpet was then subjected to the accelerated soiling procedure described below, and the Delta E was measured. The Delta E was measured using a Minolta Chroma Meter® CR-210. The standard (target) used for making each Delta E measurement was a new, unused "as-is" sample of the carpet being tested. Color readings were taken at five different areas on the carpet sample and the average Delta E was reported. In measuring the Delta E, the standard (target) value of the new, unused, "as-is" carpet sample is first measured, and this value is stored in the memory of the Chroma Meter®. The value of the soiled carpet is then measured by the Chroma Meter®, and the Delta E is calculated therefrom. Delta E color deviation represents the total color difference. A lower Delta E value means the carpet resisted resoiling better than a carpet with a higher Delta E value.

20 **Accelerated Soiling Procedure** - A drum mill (on rollers) is used to tumble synthetic soil onto the carpet. Synthetic soil is prepared as described in AATCC Test Method 123-1995, Section 8. The synthetic soil contains 38% dark peat moss, 17% portland cement, 17% kaolin clay, 17% 76 µm (200 mesh) silica, 1.75% carbon black (lamp or furnace black), 0.50% red iron oxide and 8.75% mineral oil (medicinal grade). All percentages are weight percent based on total weight of the soil.

25 **Preparation of soil-coated beads** - Place 30 grams of synthetic soil and 1 liter of clean nylon resin beads (Surlyn® ionomer resin beads 3.2-4.8 mm (1/8" - 3/16") diameter) into a clean, empty canister. Close the canister lid. Seal with duct tape and rotate the canister on rollers for 5 minutes. Remove the soil-coated beads from the canister.

30 **Preparation of carpet samples to insert into the drum** - Total sample size was 20.32cm x 63.5cm (8" x 25") for these tests. One test item and one control item are tested at the same time. The carpet pile of all samples must lay in the same direction. Cut the 20.32 cm (8") side of the carpets in the machine direction (with the tuft rows).

35 [0025] In order to soil the carpet samples, place strong adhesive tape on the back side of the carpet pieces to hold them together. Place the carpet samples in the clean, empty drum mill with the tufts facing toward the center of the drum. The carpet is held in place in the drum mill with rigid wires. Place 250 cm³ of soil-coated resin beads and 250 cm³ of ball bearings 0.8cm (5/16") diameter) into the drum mill. Close the drum mill lid and seal with duct tape. Run the drum on the rollers for 2 1/2 minutes at 105 rev/min. Stop the rollers and reverse the direction of the drum mill. Run the drum on the rollers for an additional 2 1/2 minutes at 105 rev/min. Remove the carpet samples. Vacuum the carpet uniformly to remove excess dirt. Discard the soil-coated beads.

40

EXAMPLES

45 [0026] Although all the examples below illustrate the use of the textile fabric cleaning compositions of this invention in cleaning carpets, it will be readily recognized by one skilled in the art that the cleaning formulations of this invention have utility in cleaning other textile fabrics such as upholstery. In all the examples, cleaning was by hot water extraction.

[0027] The cleaning formulations shown in Table I were prepared and used in the examples. All weights of chemical components (detergent, soil-resist agent, stain-resist agent, and colloidal metal complex) shown in Table I are in grams per liter of formulation. Water was used as the solvent.

50

TABLE I

(Grams/Liter of Aqueous Cleaning Formulation)				
Formulation	Detergent	Soil Resist	Stain Resist	Colloidal Metal Complex
Control A	1.1g SS-76®	-	-	-
Control B	1.1g SS-76®	70.5g	140.8g	-
		ZONYL®	ZELAN®	-

55

TABLE I (continued)

(Grams/Liter of Aqueous Cleaning Formulation)				
Formulation	Detergent	Soil Resist	Stain Resist	Colloidal Metal Complex
		7950	338	
Sample 1	1.1g SS-76®	35.2g	140.8g	133g
		ZOMYL®	ZELAN®	LUDOX®
		7950	338	HS-40
Sample 2	1.1g SS-76®	52.8g	211.3g	52.8g
		ZONYL®	ZELAN®	LUDOX®
		7950	338	HS-40
Sample 3	1.1g SS-76®	26.4g	105.6g	26.4g
		ZONYL®	ZELAN®	LUDOX®
		7950	338	HS-40
Sample 4	1.1g SS-76®	52.8g	211.3g	52.8g
		ZONYL®	ZELAN®	LUDOX®
		5180	338	HS-40
Control C	1.1g SS-76®	-	140.8g	35.2g
			ZELAN®	LUDOX®
			338	HS-40
Control D	1.1g sodium lauryl sulfate	-	-	-
Sample 5	1.1g sodium	35.5g	140.8g	35.5g
	lauryl sulfate	ZONYL®	ZELAN®	LUDOX®
		7950	338	HS-40

Example 1

[0028] The carpet used in this example was a new, never-used beige level loop commercially available carpet 882 g/m² (26 oz./sq. yd.) having a nylon 6,6 face fiber. The carpet did not have any fluorochemical or stain-resist treatment prior to being cleaned.

[0029] Carpets were cleaned with control cleaning formulations and cleaning formulations of this invention. After cleaning, the carpets were stained and their ability to resist stains measured according to the test method. Results are shown in Table II.

TABLE II

Formulation	Stain Rating
Control A	2
Control B	7
Sample 1	7

[0030] The stain rating of carpets cleaned with the formulations of this invention (Sample 1) is at least as good as the rating of carpets cleaned with the prior art fabric cleaning formulation containing fluorochemical and stain-resist, but no colloidal metal complex (Control B). Both formulations provide much better stain-resistance than Control A (detergent with no fluorochemical or stain-resist additives).

[0031] A second set of carpets were cleaned with control and cleaning formulations of this invention and then the carpets were subjected to an accelerated soiling test as described in the above test methods. Results are shown in Table III.

TABLE III

Soiling Performance			
ΔE of Carpet Treated with Control and Test Formulation Samples vs. New Carpet			
Formulation:	Control A	Control B	Sample 1
	19.1	15.2	
	16.4		7.3

[0032] The carpets cleaned with the formulation of this invention (Sample 1) soiled significantly less (smaller delta E) than carpets cleaned with the Control A.

Example 2

[0033] The effect of carpet construction (including pretreatments with stain or soil-resists) on the ability of the cleaning formulations of this invention to prevent re-soiling was determined in this example. Three different carpets were used: "Carpet A" was a light beige level loop commercial carpet having nylon 6,6 face fiber and treated by the mill with a topical fluorochemical soil-resist. "Carpet B" was a yellow cut pile commercial carpet having nylon 6,6 face fiber and treated with a topical fluorochemical soil-resist by the mill. "Carpet C" was a light beige level loop commercial carpet having nylon 6,6 solution dyed face fiber and was not treated by the mill with a fluorochemical soil-resist. Results of the accelerated soiling test are shown in Table IV.

TABLE IV

Soiling Performance				
ΔE of Carpet Treated with Control and Test Formulation Samples vs. New Carpet				
Carpet A				
Formulation:	Control A	Sample 2	Sample 3	Sample 4
	12.1	6.4		
	11.3		6.7	
	11.5			6.6
Carpet B				
Formulation:	Control A	Sample 2	Sample 3	Sample 4
	30.7	18.1		
	35.3		19.9	
	32.1			18.0
Carpet C				
Formulation:	Control A	Sample 2	Sample 3	Sample 4
	13.9	5.9		
	12.5		5.9	
	11.7			6.6

[0034] Carpets cleaned with the cleaning formulations of this invention (Samples 2-4) resoiled significantly less than carpets cleaned with the control formulation. The improvement in resoiling using the formulations of this invention was evident regardless of whether the carpet had originally been treated with fluorochemical prior to cleaning.

Example 3

[0035] The necessity for having a fluorochemical soil-resist in the cleaning formulations of this invention was demonstrated in this example.

[0036] Yellow level loop commercial carpet 882 g/m² (26 oz./sq. yd.) having a nylon 6,6 face fiber which had not been treated with fluorochemical stain-resist by the mill was used in this example. Carpet was subjected to the accel-

erated soiling procedure and soil performance test method described above. Results are contained in Table V.

TABLE V

Soiling Performance			
ΔE of Carpet Treated with Control and Test Formulation Samples vs. New Carpet			
Formulation:	Control A	Sample 1	Control C
	54.4	12.1	28.2
	52.9		

[0037] Control C contained a stain-resist agent and a colloidal metal complex, but no fluorochemical soil-resist. Its ability to prevent resoiling was significantly worse ($\Delta E = 28.2$) than a formulation of this invention (Sample 1) which contained fluorochemical soil-resist, stain-resist and colloidal metal complex ($\Delta E = 12.1$).

Example 4

[0038] The effect of changing detergent type (sodium lauryl sulfate mixture vs. sodium tripolyphosphate/sodium sesquicarbonate) on restaining and resoiling was investigated in this example. New pieces of the same carpet used in Example 3 were used in this example. The results of the stain test are contained in Table VI and the resoiling test are contained in Table VII.

TABLE VI

Stain Performance After Cleaning	
Formulation	Stain Rating
Control A	1
Control D	1
Sample 5	9

TABLE VII

Soiling Performance After Cleaning			
ΔE of Carpet Treated with Control and Test Formulation Samples vs. New Carpet			
Formulation:	Control A	Control D	Sample 5
	53.7		14.5
		52.2	13.4

[0039] The cleaning formulations of this invention perform just as well in the stain test and soiling test regardless of whether the detergent is sodium tripolyphosphate/sodium sesquicarbonate or sodium lauryl sulfate mixture.

Example 5

[0040] This example measured the effect of cleaning formulations of this invention on the resoiling of nylon 6 carpets. The carpet used was a light gray commercial level loop style carpet having nylon 6 face fiber. The face fiber had been treated with a fluorochemical soil-resist by the mill. Rather than using the accelerated soiling procedure described in the test method, carpet was first trafficked in a busy corridor of an office building for 260,000 human foot traffics. The carpet was then cleaned with a control cleaning formulation and a cleaning formulation of this invention and then exposed to an additional 91,000 human foot traffics. The resoiling performance is shown in Table VIII.

TABLE VIII

Soiling Performance After Cleaning		
ΔE of Carpet Treated with Control and Test Formulation Samples vs. New Carpet		
Formulation:	Control A	Sample 1
	13.0	8.0

[0041] Thus the cleaning formulations of this invention work on nylon 6 carpets as well as nylon 6,6 carpets to prevent resoiling.

Example 6

[0042] The minimum useful level of ingredients was determined in this example.

[0043] The carpet used in this example was new, never used yellow level loop commercial carpet 882g/m² (26 oz/sq.yd.) having a nylon 6,6 face fiber. The carpet did not have any fluorochemical or stain-resist treatment prior to being cleaned.

[0044] Carpets were cleaned with control cleaning formulation and cleaning formulations of this invention. After cleaning, the carpets were stained and their ability to resist stains was measured according to the test method. The stain rating of carpets 442-2, 430-6, 430-5, 430-4, 430-3, 430-2, 404-6, 404-5, 404-4, 404-3, and 404-2 were better than control.

[0045] These carpets were also subjected to an accelerated soiling test as described in the above methods. The carpets cleaned with the formulations of this invention soiled significantly less (smaller delta E) than carpets cleaned with the control. Restain and resoil data are contained in TABLE IX.

TABLE IX

		(Grams/Liter of Formulation)				DELTA E DRUM SOIL		1 HR KOOL-AID®
ITEM	SS-76®	ZONYL® 7950	LUDOX® HS-40	ZELAN® 338	CONT SS-76®	TEST ITEM	STAIN- TEST	
Control	1.1						1	
A								
404-2	1.1	35.2	35.2	140.8	54.4	12.1	4.5	
404-3	1.1	17.6	17.6	70.4	56.2	13.9	4	
404-4	1.1	8.8	8.8	35.2	55.9	17.5	4	
404-5	1.1	4.4	4.4	17.6	58.5	21.5	3.5	
404-6	1.1	2.2	2.2	8.8	54.1	22.2	3.5	
430-2	1.1	1.7	1.7	6.6	48.3	20.3	2.5	
430-3	1.1	0.8	0.8	3.3	49.5	32.5	2.5	
430-4	1.1	0.4	0.4	1.7	50.7	38.8	2.5	
430-5	1.1	0.2	0.2	0.8	50.4	44.4	2	
430-6	1.1	0.1	0.1	0.4	51.0	47.7	2	
442-2	1.1	0.05	0.05	0.2	58.4	49.3	1.5	
*442-3	1.1	0.025	0.025	0.1	57.2	54.4	1	
*442-4	1.1	0.013	0.013	0.05	59.0	56.3	1	

* not in accordance with this invention.

Claims

1. An aqueous cleaning formulation comprising:

- (a) 4 to 270 grams of a detergent per 3.79l (gallon) of cleaning formulation,
- (b) 0.04 to 133 grams of a fluorochemical soil-resist agent per 3.79l (gallon) of cleaning formulation,
- (c) 0.7 to 536 grams of a stain-resist agent per 3.79l (gallon) of cleaning formulation, and
- (d) 0.04 to 133 grams of inorganic particulate matter selected from the group consisting of clays, colloidal silica, colloidal alumina, titanium dioxide, and mixtures thereof per 3.79l (gallon) of cleaning formulation.

2. An aqueous cleaning formulation comprising:

- (a) 1.3 to 270 grams of a detergent per 3.79l (gallon) of cleaning formulation,
- (b) 0.009 to 60 grams of a fluorochemical soil-resist agent per 3.79l (gallon) of cleaning formulation,
- (c) 0.2 to 134 grams of a stain-resist agent per 3.79l (gallon) of cleaning formulation, and
- (d) 0.01 to 53 grams of inorganic particulate matter selected from the group consisting of clays, colloidal silica, colloidal alumina, titanium dioxide, and mixtures thereof per 3.79l (gallon) of cleaning formulation.

3. The aqueous cleaning formulation of claim 1 or 2, wherein the detergent comprises an anionic, cationic, amphoteric, or nonionic surfactant.

4. The aqueous cleaning formulation of claim 3, wherein the detergent is selected from the group consisting of a mixture of sodium tripolyphosphate and sodium sesquicarbonate; and a mixture of sodium lauryl sulfate, sodium hexadecyl sulfate, and sodium tetradecyl sulfate.

5. The aqueous cleaning formulation of claim 1 or 2, wherein the stain-resist agent is a compound selected from the group consisting of copolymers of hydrolyzed maleic anhydride with aliphatic alpha olefins, aromatic olefins, or vinyl ethers, homopolymers of methacrylic acid, and copolymers of methacrylic acid.

6. The aqueous cleaning formulation of claim 4, wherein the detergent is a mixture of sodium tripolyphosphate and sodium sesquicarbonate, and the inorganic particulate matter is colloidal silica.

7. The aqueous cleaning formulation of claim 4, wherein the detergent is a mixture of sodium lauryl sulfate, sodium hexadecyl sulfate, and sodium tetradecyl sulfate, and the inorganic particulate matter is colloidal silica.

8. A cleaning concentrate suitable for making an aqueous cleaning formulation comprising: (a) a detergent, (b) a fluorochemical soil-resist agent, (c) a stain-resist agent, and (d) inorganic particulate matter selected from the group consisting of clays, colloidal silica, colloidal alumina, titanium dioxide, and mixtures thereof, whereby the concentrate is capable of being diluted with an appropriate amount of water to produce an aqueous cleaning formulation having a concentration of 4 to 270 grams of a detergent per 3.79l (gallon) of cleaning formulation, 0.04 to 133 grams of a fluorochemical soil-resist agent per 3.79l (gallon) of cleaning formulation, 0.7 to 536 grams of a stain-resist agent per 3.79l (gallon) of cleaning formulation, and 0.04 to 133 grams of inorganic particulate matter per 3.79l (gallon) of cleaning formulation.

9. A cleaning concentrate suitable for making an aqueous cleaning formulation comprising: (a) a detergent, (b) a fluorochemical soil-resist agent, (c) a stain-resist agent, and (d) inorganic particulate matter selected from the group consisting of clays, colloidal silica, colloidal alumina, titanium dioxide, and mixtures thereof, whereby the concentrate is capable of being diluted with an appropriate amount of water to produce an aqueous cleaning formulation having a concentration of 1.3 to 270 grams of a detergent per 3.79l (gallon) of cleaning formulation, 0.009 to 60 grams of a fluorochemical soil-resist agent per 3.79l (gallon) of cleaning formulation, 0.2 to 134 grams of a stain-resist agent per 3.79l (gallon) of cleaning formulation, and 0.01 to 53 grams of inorganic particulate matter per 3.79l (gallon) of cleaning formulation.

10. The cleaning concentrate of claim 8 or 9, wherein the detergent comprises an anionic, cationic, amphoteric, or nonionic surfactant.
- 5 11. The cleaning concentrate of claim 10, wherein the detergent is selected from the group consisting of a mixture of sodium tripolyphosphate and sodium sesquicarbonate; and a mixture of sodium lauryl sulfate, sodium hexadecyl sulfate and sodium tetradecyl sulfate.
- 10 12. The cleaning concentrate of claim 8 or 9, wherein the stain-resist agent is a compound selected from the group consisting of copolymers of hydrolyzed maleic anhydride with aliphatic alpha olefins, aromatic olefins, or vinyl ethers, homopolymers of methacrylic acid, and copolymers of methacrylic acid.
13. The cleaning concentrate of claim 8 or 9, wherein the detergent is a mixture of sodium tripolyphosphate and sodium sesquicarbonate, and the inorganic particulate matter is colloidal silica.
- 15 14. The cleaning concentrate of claim 8 or 9, wherein the detergent is a mixture of sodium lauryl sulfate, sodium hexadecyl sulfate and sodium tetradecyl sulfate, and the inorganic particulate matter is colloidal silica.
- 20 15. A method for cleaning a textile fabric comprising fibers having soil on the surface of the fibers, comprising the steps of:
 - (a) contacting the fibers with an aqueous cleaning formulation comprising a detergent, a fluorochemical soil-resist agent, a stain-resist agent, and inorganic particulate matter selected from the group consisting of clays, colloidal silica, colloidal alumina, titanium dioxide, and mixtures thereof in a concentration of: (i) 0.07 to 5% of detergent based on weight of fiber, (ii) 0.0008 to 10% of fluorochemical soil-resist agent based on weight of fiber, (iii) 0.01 to 15% of stain-resist agent based on weight of fiber, and (iv) 0.0008 to 10% of inorganic particulate matter based on weight of fiber in such a manner that at least some of the soil is loosened, and (b) removing at least some of the loosened soil.
- 25 16. A method for cleaning a textile fabric comprising fibers having soil on the surface of the fibers, comprising the steps of:
 - (a) contacting the fibers with an aqueous cleaning formulation comprising a detergent, a fluorochemical soil-resist agent, a stain-resist agent, and inorganic particulate matter selected from the group consisting of clays, colloidal silica, colloidal alumina, titanium dioxide, and mixtures thereof in a concentration of: (i) 0.02 to 5% of detergent based on weight of fiber, (ii) 0.0002 to 4.5% of fluorochemical soil-resist agent based on weight of fiber, (iii) 0.0025 to 3.75% of stain-resist agent based on weight of fiber, and (iv) 0.0003 to 4.0% of inorganic particulate matter based on weight of fiber in such a manner that at least some of the soil is loosened, and (b) removing at least some of the loosened soil.
- 30 17. The method of claim 15 or 16, wherein the detergent in the cleaning formulation comprises an anionic, cationic, amphoteric, or nonionic surfactant.
18. The method of claim 17, wherein the detergent is selected from the group consisting of a mixture of sodium tripolyphosphate and sodium sesquicarbonate; and a mixture of sodium lauryl sulfate, sodium hexadecyl sulfate, and sodium tetradecyl sulfate.
- 35 19. The method of claim 15 or 16, wherein the stain-resist agent in the cleaning formulation is a compound selected from the group consisting of copolymers of hydrolyzed maleic anhydride with aliphatic alpha olefins, aromatic olefins, or vinyl ethers, homopolymers of methacrylic acid, and copolymers of methacrylic acid.
- 40 20. The method of claim 15 or 16, wherein the detergent in the cleaning formulation is a mixture of sodium tripolyphosphate and sodium sesquicarbonate, and the inorganic particulate matter is colloidal silica.
- 45 21. The method of claim 15 or 16, wherein the detergent in the cleaning formulation is a mixture of sodium lauryl sulfate, sodium hexadecyl sulfate, and sodium tetradecyl sulfate, and the inorganic particulate matter is colloidal silica.
- 50 22. The method of claim 15 or 16, wherein the fibers are contacted with the aqueous cleaning formulation by spraying
- 55

the formulation having a temperature in the range of room temperature to 71°C (160°F) onto the fibers.

23. The method of claim 15 or 16, wherein the fibers are contacted with the aqueous cleaning formulation by foaming the formulation onto the fibers.

24. The method of claim 15 or 16, wherein the fibers are contacted with the aqueous cleaning formulation by contacting the fibers with a device containing with the formulation.

25. The method of claim 15 or 16, wherein the textile fabric is a carpet.

26. The method of claim 25, wherein the carpet is a nylon carpet.

Patentansprüche

1. Wässrige Reinigungsformulierung, umfassend:

(a) 4 bis 270 Gramm eines Waschmittels pro 3,79 l (Gallone) der Reinigungsformulierung,

(b) 0,04 bis 133 Gramm eines fluorchemischen schmutzbeständigen Mittels pro 3,79 l (Gallone) der Reinigungsformulierung,

(c) 0,7 bis 536 Gramm eines fleckenbeständigen Mittels pro 3,79 l (Gallone) der Reinigungsformulierung, und

(d) 0,04 bis 133 Gramm anorganisches teilchenförmiges Material, ausgewählt aus der Gruppe, bestehend aus Tonen, kolloidalem Siliciumdioxid, kolloidalem Aluminiumoxid, Titandioxid und Gemischen davon, pro 3,79 l (Gallone) der Reinigungsformulierung.

2. Wässrige Reinigungsformulierung, umfassend:

(a) 1,3 bis 270 Gramm eines Waschmittels pro 3,79 l (Gallone) der Reinigungsformulierung,

(b) 0,009 bis 60 Gramm eines fluorchemischen schmutzbeständigen Mittels pro 3,79 l (Gallone) der Reinigungsformulierung,

(c) 0,2 bis 134 Gramm eines fleckenbeständigen Mittels pro 3,79 l (Gallone) der Reinigungsformulierung, und

(d) 0,01 bis 53 Gramm anorganisches teilchenförmiges Material, ausgewählt aus der Gruppe, bestehend aus Tonen, kolloidalem Siliciumdioxid, kolloidalem Aluminiumoxid, Titandioxid und Gemischen davon, pro 3,79 l (Gallone) der Reinigungsformulierung.

3. Wässrige Reinigungsformulierung nach Anspruch 1 oder 2, wobei das Waschmittel ein anionisches, kationisches, amphoterisches oder nichtionisches Tensid umfaßt.

4. Wässrige Reinigungsformulierung nach Anspruch 3, wobei das Waschmittel aus der Gruppe, bestehend aus einem Gemisch von Natriumtripolyphosphat und Natriumsesquicarbonat; und einem Gemisch von Natriumlaurylsulfat, Natriumhexadecylsulfat und Natriumtetradecylsulfat, ausgewählt ist.

5. Wässrige Reinigungsformulierung nach Anspruch 1 oder 2, wobei das fleckenbeständige Mittel eine Verbindung ist, ausgewählt aus der Gruppe, bestehend aus Copolymeren von hydrolysiertem Maleinsäureanhydrid mit aliphatischen alpha-Olefinen, aromatischen Olefinen oder Vinylethern, Homopolymeren von Methacrylsäure und Copolymeren von Methacrylsäure.

6. Wässrige Reinigungsformulierung nach Anspruch 4, wobei das Waschmittel ein Gemisch von Natriumtripolyphosphat und Natriumsesquicarbonat ist und das anorganische teilchenförmige Material kolloidales Siliciumdioxid ist.

7. Wässrige Reinigungsformulierung nach Anspruch 4, wobei das Waschmittel ein Gemisch von Natriumlaurylsulfat, Natriumhexadecylsulfat und Natriumtetradecylsulfat ist und das anorganische teilchenförmige Material kolloidales Siliciumdioxid ist.

8. Reinigungskonzentrat, geeignet zur Herstellung einer wässrigen Reinigungsformulierung, umfassend: (a) ein Waschmittel, (b) ein fluorchemisches schmutzbeständiges Mittel, (c) ein fleckenbeständiges Mittel und (d) anorganisches teilchenförmiges Material, ausgewählt aus der Gruppe, bestehend aus Tonen, kolloidalem Siliciumdi-

oxid, kolloidalem Aluminiumoxid, Titandioxid und Gemischen davon, wobei das Konzentrat imstande ist, mit einer geeigneten Menge von Wasser verdünnt zu werden, um eine wässrige Reinigungsformulierung mit einer Konzentration von 4 bis 270 Gramm eines Waschmittels pro 3,79 l (Gallone) der Reinigungsformulierung, 0,04 bis 133 Gramm eines fluorchemischen schmutzbeständigen Mittels pro 3,79 l (Gallone) der Reinigungsformulierung, 0,7 bis 536 Gramm eines fleckenbeständigen Mittels pro 3,79 l (Gallone) der Reinigungsformulierung und 0,04 bis 133 Gramm von anorganischem teilchenförmigen Material pro 3,79 l (Gallone) der Reinigungsformulierung zu erzeugen.

9. Reinigungskonzentrat, geeignet zur Herstellung einer wässrigen Reinigungsformulierung, umfassend: (a) ein Waschmittel, (b) ein fluorchemisches schmutzbeständiges Mittel, (c) ein fleckenbeständiges Mittel und (d) anorganisches teilchenförmiges Material, ausgewählt aus der Gruppe, bestehend aus Tonen, kolloidalem Siliciumdioxid, kolloidalem Aluminiumoxid, Titandioxid und Gemischen davon, wobei das Konzentrat imstande ist, mit einer geeigneten Menge von Wasser verdünnt zu werden, um eine wässrige Reinigungsformulierung mit einer Konzentration von 1,3 bis 270 Gramm eines Waschmittels pro 3,79 l (Gallone) der Reinigungsformulierung, 0,009 bis 60 Gramm eines fluorchemischen schmutzbeständigen Mittels pro 3,79 l (Gallone) der Reinigungsformulierung, 0,2 bis 134 Gramm eines fleckenbeständigen Mittels pro 3,79 l (Gallone) der Reinigungsformulierung und 0,01 bis 53 Gramm von anorganischem teilchenförmigen Material pro 3,79 l (Gallone) der Reinigungsformulierung zu erzeugen.

10. Reinigungskonzentrat nach Anspruch 8 oder 9, wobei das Waschmittel ein anionisches, kationisches, amphoterisches oder nichtionisches Tensid umfaßt.

11. Reinigungskonzentrat nach Anspruch 10, wobei das Waschmittel aus der Gruppe, bestehend aus einem Gemisch von Natriumtripolyphosphat und Natriumsesquicarbonat; und einem Gemisch von Natriumlaurylsulfat, Natriumhexadecylsulfat und Natriumtetradecylsulfat, ausgewählt ist.

12. Reinigungskonzentrat nach Anspruch 8 oder 9, wobei das fleckenbeständige Mittel eine Verbindung, ausgewählt aus der Gruppe, bestehend aus Copolymeren von hydrolysiertem Maleinsäureanhydrid mit aliphatischen alpha-Olefinen, aromatischen Olefinen oder Vinylethern, Homopolymeren von Methacrylsäure und Copolymeren von Methacrylsäure, ist.

13. Reinigungskonzentrat nach Anspruch 8 oder 9, wobei das Waschmittel ein Gemisch von Natriumtripolyphosphat und Natriumsesquicarbonat ist und das anorganische teilchenförmige Material kolloidales Siliciumdioxid ist.

14. Reinigungskonzentrat nach Anspruch 8 oder 9, wobei das Waschmittel ein Gemisch von Natriumlaurylsulfat, Natriumhexadecylsulfat und Natriumtetradecylsulfat ist und das anorganische teilchenförmige Material kolloidales Siliciumdioxid ist.

15. Verfahren zum Reinigen eines textilen Gewebes, umfassend Fasern mit Schmutz auf der Oberfläche der Fasern, umfassend die Schritte:

(a) Inkontaktbringen der Fasern mit einer wässrigen Reinigungsformulierung, umfassend ein Waschmittel, ein fluorchemisches schmutzbeständiges Mittel, ein fleckenbeständiges Mittel und anorganisches teilchenförmiges Material, ausgewählt aus der Gruppe, bestehend aus Tonen, kolloidalem Siliciumdioxid, kolloidalem Aluminiumoxid, Titandioxid und Gemischen davon in einer Konzentration von: (i) 0,07 bis 5% Waschmittel, bezogen auf das Gewicht der Faser, (ii) 0,0008 bis 10% fluorchemisches schmutzbeständiges Mittel, bezogen auf das Gewicht der Faser, (iii) 0,01 bis 15% fleckenbeständiges Mittel, bezogen auf das Gewicht der Faser, und (iv) 0,0008 bis 10% anorganisches teilchenförmiges Material, bezogen auf das Gewicht der Faser, in einer derartigen Weise, daß zumindest etwas von dem Schmutz gelöst wird, und (b) Entfernen von zumindest etwas von dem gelösten Schmutz.

16. Verfahren zum Reinigen eines textilen Gewebes, umfassend Fasern mit Schmutz auf der Oberfläche der Fasern, umfassend die Schritte:

(a) Inkontaktbringen der Fasern mit einer wässrigen Reinigungsformulierung, umfassend ein Waschmittel, ein fluorchemisches schmutzbeständiges Mittel, ein fleckenbeständiges Mittel und anorganisches teilchenförmiges Material, ausgewählt aus der Gruppe, bestehend aus Tonen, kolloidalem Siliciumdioxid, kolloidalem Aluminiumoxid, Titandioxid und Gemischen davon in einer Konzentration von: (i) 0,02 bis 5% Waschmittel,

bezogen auf das Gewicht der Faser, (ii) 0,0002 bis 4,5% fluorchemisches schmutzbeständiges Mittel, bezogen auf das Gewicht der Faser, (iii) 0,0025 bis 3,75% fleckenbeständiges Mittel, bezogen auf das Gewicht der Faser, und (iv) 0,0003 bis 4,0% anorganisches teilchenförmiges Material, bezogen auf das Gewicht der Faser, in einer derartigen Weise, daß zumindest etwas von dem Schmutz gelöst wird, und (b) Entfernen von zumindest etwas von dem gelösten Schmutz.

17. Verfahren nach Anspruch 15 oder 16, wobei das Waschmittel in der Reinigungsformulierung ein anionisches, kationisches, amphoterisches oder nichtionisches Tensid umfaßt.
18. Verfahren nach Anspruch 17, wobei das Waschmittel aus der Gruppe, bestehend aus einem Gemisch von Natriumtripolyphosphat und Natriumsesquicarbonat; und einem Gemisch von Natriumlaurylsulfat, Natriumhexadecylsulfat und Natriumtetradecylsulfat, ausgewählt ist.
19. Verfahren nach Anspruch 15 oder 16, wobei das fleckenbeständige Mittel in der Reinigungsformulierung eine Verbindung ist, ausgewählt aus der Gruppe, bestehend aus Copolymeren von hydrolysiertem Maleinsäureanhydrid mit aliphatischen alpha-Olefinen, aromatischen Olefinen oder Vinylethern, Homopolymeren von Methacrylsäure und Copolymeren von Methacrylsäure.
20. Verfahren nach Anspruch 15 oder 16, wobei das Waschmittel in der Reinigungsformulierung ein Gemisch von Natriumtripolyphosphat und Natriumsesquicarbonat ist und das anorganische teilchenförmige Material kolloidales Siliciumdioxid ist.
21. Verfahren nach Anspruch 15 oder 16, wobei das Waschmittel in der Reinigungsformulierung ein Gemisch von Natriumlaurylsulfat, Natriumhexadecylsulfat und Natriumtetradecylsulfat ist und das anorganische teilchenförmige Material kolloidales Siliciumdioxid ist.
22. Verfahren nach Anspruch 15 oder 16, wobei die Fasern mit der wässrigen Reinigungsformulierung durch Sprühen der Formulierung mit einer Temperatur in dem Bereich von Raumtemperatur bis 71°C (160°F) auf die Fasern in Kontakt gebracht werden.
23. Verfahren nach Anspruch 15 oder 16, wobei die Fasern mit der wässrigen Reinigungsformulierung durch Schäumen der Formulierung auf die Fasern in Kontakt gebracht werden.
24. Verfahren nach Anspruch 15 oder 16, wobei die Fasern mit der wässrigen Reinigungsformulierung durch Inkontaktingen der Fasern mit einer Vorrichtung, enthaltend die Formulierung, in Kontakt gebracht werden.
25. Verfahren nach Anspruch 15 oder 16, wobei das textile Gewebe ein Teppich ist.
26. Verfahren nach Anspruch 25, wobei der Teppich ein Nylonteppich ist.

Revendications

1. Formulation nettoyante aqueuse comprenant:

- (a) de 4 à 270 grammes d'un détergent pour 3,79 l (1 gallon) de formulation nettoyante;
- (b) de 0,04 à 133 grammes d'un agent anti-salissure fluorochimique pour 3,79 l (1 gallon) de formulation nettoyante;
- (c) de 0,7 à 536 grammes d'un agent anti-tache pour 3,79 l (1 gallon) de formulation nettoyante; et
- (d) de 0,04 à 133 grammes d'une matière particulaire inorganique choisie dans le groupe constitué d'argiles, de silice colloïdale, d'alumine colloïdale, de dioxyde de titane et de mélanges de ceux-ci pour 3,79 l (1 gallon) de formulation nettoyante.

2. Formulation nettoyante aqueuse comprenant:

- (a) de 1,3 à 270 grammes d'un détergent pour 3,79 l (1 gallon) de formulation nettoyante;
- (b) de 0,009 à 60 grammes d'un agent anti-salissure fluorochimique pour 3,79 l (1 gallon) de formulation nettoyante;

(c) de 0,2 à 134 grammes d'un agent de anti-tache pour 3,79 l (1 gallon) d formulation nettoyante; et
(d) de 0,01 à 53 grammes d'une matière particulaire inorganique choisie dans le groupe constitué d'argiles, de silice colloïdale, d'alumine colloïdale, de dioxyde de titane et de mélanges de ceux-ci pour 3,79 l (1 gallon) de formulation nettoyante.

- 5 3. Formulation nettoyante aqueuse suivant la revendication 1 ou 2, dans laquelle le détergent comprend un tensioactif anionique, cationique, amphotère ou non ionique.
- 10 4. Formulation nettoyante aqueuse suivant la revendication 3, dans laquelle le détergent est choisi dans le groupe constitué d'un mélange de tripolyphosphate de sodium et de sesquicarbonate de sodium; et d'un mélange de sulfate de lauryle de sodium, de sulfate d'hexadécyle de sodium et de sulfate de tétradécyle de sodium.
- 15 5. Formulation nettoyante aqueuse suivant la revendication 1 ou 2, dans laquelle l'agent anti-tache est un composé choisi dans le groupe constitué de copolymères d'anhydride maléique hydrolysé avec des alpha-oléfines aliphatiques, des oléfines aromatiques ou des vinyléthers, d'homopolymères d'acide méthacrylique et de copolymères d'acide méthacrylique.
- 20 6. Formulation nettoyante aqueuse suivant la revendication 4, dans laquelle le détergent est un mélange de tripolyphosphate de sodium et de sesquicarbonate de sodium, et la matière particulaire inorganique est une silice colloïdale.
- 25 7. Formulation nettoyante aqueuse suivant la revendication 4, dans laquelle le détergent est un mélange de sulfate de lauryle de sodium, de sulfate d'hexadécyle de sodium et de sulfate de tétradécyle de sodium, et la matière particulaire inorganique est une silice colloïdale.
- 30 8. Concentré nettoyant approprié pour la fabrication d'une formulation nettoyante aqueuse comprenant: (a) un détergent, (b) un agent anti-salissure fluorochimique, (c) un agent anti-tache et (d) une matière particulaire inorganique choisie dans le groupe constitué d'argiles, de silice colloïdale, d'alumine colloïdale, de dioxyde de titane et de mélanges de ceux-ci, en conséquence de quoi le concentré est capable d'être dilué avec une quantité appropriée d'eau pour produire une formulation nettoyante aqueuse présentant une concentration de 4 à 270 grammes d'un détergent pour 3,79 l (1 gallon) de formulation nettoyante; de 0,04 à 133 grammes d'un agent anti-salissure fluorochimique pour 3,79 l (1 gallon) de formulation nettoyante; de 0,7 à 536 grammes d'un agent anti-tache pour 3,79 l (1 gallon) de formulation nettoyante; et de 0,04 à 133 grammes d'une matière particulaire inorganique pour 3,79 l (1 gallon) de formulation nettoyante.
- 35 9. Concentré nettoyant approprié pour la fabrication d'une formulation nettoyante aqueuse comprenant: (a) un détergent, (b) un agent anti-salissure fluorochimique, (c) un agent anti-tache et (d) une matière particulaire inorganique choisie dans le groupe constitué d'argiles, de silice colloïdale, d'alumine colloïdale, de dioxyde de titane et de mélanges de ceux-ci, en conséquence de quoi le concentré est capable d'être dilué avec une quantité appropriée d'eau pour produire une formulation nettoyante aqueuse présentant une concentration de 1,3 à 270 grammes d'un détergent pour 3,79 l (1 gallon) de formulation nettoyante; de 0,009 à 60 grammes d'un agent anti-salissure fluorochimique pour 3,79 l (1 gallon) de formulation nettoyante; de 0,2 à 134 grammes d'un agent anti-tache pour 3,79 l (1 gallon) de formulation nettoyante; et de 0,01 à 53 grammes d'une matière particulaire inorganique pour 3,79 l (1 gallon) de formulation nettoyante.
- 40 10. Concentré nettoyant suivant la revendication 8 ou 9, dans lequel le détergent comprend un tensioactif anionique, cationique, amphotère ou non ionique.
- 45 11. Concentré nettoyant suivant la revendication 10, dans lequel le détergent est choisi dans le groupe constitué d'un mélange de tripolyphosphate de sodium et de sesquicarbonate de sodium; et d'un mélange de sulfate de lauryle de sodium, de sulfate d'hexadécyle de sodium et de sulfate de tétradécyle de sodium.
- 50 12. Concentré nettoyant suivant la revendication 8 ou 9, dans lequel l'agent anti-tache est un composé choisi dans le groupe constitué de copolymères d'anhydride maléique hydrolysé avec des alpha-oléfines aliphatiques, des oléfines aromatiques ou des vinyléthers, d'homopolymères d'acide méthacrylique et de copolymères d'acide méthacrylique.
- 55 13. Concentré nettoyant suivant la revendication 8 ou 9, dans lequel le détergent est un mélange de tripolyphosphate

de sodium et de sesquicarbonate de sodium, et la matière particulaire inorganique est une silice colloïdale.

14. Concentré nettoyant suivant la revendication 8 ou 9, dans lequel le détergent est un mélange de sulfate de lauryle de sodium, de sulfate d'hexadécyle de sodium et de sulfate de tétradécyle de sodium, et la matière particulaire inorganique est une silice colloïdale.

15. Procédé pour le nettoyage d'un tissu textile comprenant des fibres avec une salissure sur la surface des fibres, comprenant les étapes:

- (a) de contact des fibres avec une formulation nettoyante aqueuse comprenant un détergent, un agent anti-salissure fluorochimique, un agent anti-tache et une matière particulaire inorganique choisie dans le groupe constitué d'argiles, de silice colloïdale, d'alumine colloïdale, de dioxyde de titane et de mélanges de ceux-ci, dans une concentration: (i) de 0,07 à 5% de détergent sur la base du poids des fibres, (ii) de 0,0008 à 10% d'agent anti-salissure fluorochimique sur la base du poids des fibres, (iii) de 0,01 à 15% d'agent anti-tache sur la base du poids des fibres et (iv) de 0,0008 à 10% de matière particulaire inorganique sur la base du poids des fibres d'une manière telle qu'au moins une partie de la salissure est décollée, et
- (b) de retrait d'au moins une partie de la salissure décollée.

16. Procédé pour le nettoyage d'un tissu textile comprenant des fibres avec une salissure sur la surface des fibres, comprenant les étapes:

- (a) de contact des fibres avec une formulation nettoyante aqueuse comprenant un détergent, un agent anti-salissure fluorochimique, un agent anti-tache et une matière particulaire inorganique choisie dans le groupe constitué d'argiles, de silice colloïdale, d'alumine colloïdale, de dioxyde de titane et de mélanges de ceux-ci, dans une concentration: (i) de 0,02 à 5% de détergent sur la base du poids des fibres, (ii) de 0,0002 à 4,5% d'agent anti-salissure fluorochimique sur la base du poids des fibres, (iii) de 0,0025 à 3,75% d'agent anti-tache sur la base du poids des fibres et (iv) de 0,0003 à 4,0% de matière particulaire inorganique sur la base du poids des fibres d'une manière telle qu'au moins une partie de la salissure est décollée, et
- (b) de retrait d'au moins une partie de la salissure décollée.

17. Procédé suivant la revendication 15 ou 16, dans lequel le détergent dans la formulation nettoyante comprend un tensioactif anionique, cationique, amphotère ou non ionique.

18. Procédé suivant la revendication 17, dans lequel le détergent est choisi dans le groupe constitué d'un mélange de tripolyphosphate de sodium et de sesquicarbonate de sodium; et d'un mélange de sulfate de lauryle de sodium, de sulfate d'hexadécyle de sodium et de sulfate de tétradécyle de sodium.

19. Procédé suivant la revendication 15 ou 16, dans lequel l'agent anti-tache dans la formulation nettoyante est un composé choisi dans le groupe constitué de copolymères d'anhydride maléique hydrolysé avec des alpha-oléfines aliphatiques, des oléfines aromatiques ou des vinyléthers, d'homopolymères d'acide méthacrylique et de copolymères d'acide méthacrylique.

20. Procédé suivant la revendication 15 ou 16, dans lequel le détergent dans la formulation nettoyante est un mélange de tripolyphosphate de sodium et de sesquicarbonate de sodium, et la matière particulaire inorganique est une silice colloïdale.

21. Procédé suivant la revendication 15 ou 16, dans lequel le détergent dans la formulation nettoyante est un mélange de sulfate de lauryle de sodium, de sulfate d'hexadécyle de sodium et de sulfate de tétradécyle de sodium, et la matière particulaire inorganique est une silice colloïdale.

22. Procédé suivant la revendication 15 ou 16, dans lequel les fibres sont mises en contact avec la formulation nettoyante aqueuse en pulvérisant la formulation avec une température dans l'intervalle de la température ambiante à 71°C (160°F) sur les fibres.

23. Procédé suivant la revendication 15 ou 16, dans lequel les fibres sont mises en contact avec la formulation nettoyante aqueuse en faisant mousser la formulation sur les fibres.

24. Procédé suivant la revendication 15 ou 16, dans lequel les fibres sont mises en contact avec la formulation net-

EP 0 922 082 B1

toyante aqueus en mettant en contact les fibres avec un dispositif contenant la formulation.

25. Procédé suivant la revendication 15 ou 16, dans lequel le tissu textile est un tapis.

5 26. Procédé suivant la revendication 25, dans lequel le tapis est un tapis de nylon.

10

15

20

25

30

35

40

45

50

55